

2755 四层钢丝缠绕软管

EN 856 4SP



# 零件号	 软管内径		 软管外径		 最大工作压力		 最小爆破压力		 最小弯曲半径		 软管重量	
	mm	in	mm	in	bar	psi	bar	psi	mm	in	Kg/m	lbs/ft
2755-6	9,5	0.37	21,4	0.84	490,0	7105	1960,0	28420	180,0	7.09	0,80	0.53
2755-8	12,7	0.50	24,6	0.97	420,0	6090	1680,0	24360	230,0	9.06	0,92	0.61
2755-10	15,9	0.63	28,2	1.11	400,0	5800	1600,0	23200	250,0	9.84	1,000	0.67
2755-12	19,0	0.75	32,2	1.27	380,0	5510	1520,0	22040	300,0	11.81	1,50	1.00
2755-16	25,4	1.00	39,7	1.56	320,0	4640	1280,0	18560	340,0	13.78	2,15	1.43

结构

丁腈合成橡胶内层，四层钢丝缠绕增强层，氯丁合成橡胶外层。

工作温度范围

-40°C到+100°C[-40°F到+212°F]

最高温度120°C

应用

使用石油基流体的高压液压系统。有关特殊流体的应用和高温指标的更多资料，请参见第21页。